

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0055	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	1310	MPa	ASTM D 790
Shore D Hardness	76	-	ASTM D 2240
Tensile Strength at Break	40.1	MPa	ASTM D 412
Elongation at Break	380	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1210	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America