

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	5.17	MPa	ASTM D 412
Modulus at 300% Elongation	2.53	MPa	ASTM D 412
Shore A Hardness	82	-	ASTM D 2240
Tear Strength	70	kN/m	ASTM D 624

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	120	°C	ASTM D 3418
Glass Transition Temperature	-50	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Density	1130	kg/m ³	ASTM D 792

Characteristics**Processing**

Blown Film Extrusion, Film Extrusion, Wire/Cable Extrusion, Other Extrusion

Delivery form

Pellets

Chemical Resistance

Hydrolytically Stable

Regional Availability

North America, Europe, Asia Pacific