

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	11.8	MPa	ASTM D 412
Modulus at 300% Elongation	6.87	MPa	ASTM D 412
Shore A Hardness	94	-	ASTM D 2240
Tear Strength	113	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	15	%	ASTM D 395
Compression Set , 22 hr @ 158 °F	60	%	ASTM D 395

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	105	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion, Blow Molding

Regional Availability

North America, Europe, Asia Pacific