

MIRATHANE® A285

TPU

Miracell Chemicals Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	7	MPa	ASTM D 412
Modulus at 300% Elongation	15	MPa	ASTM D 412
Shore A Hardness	83	-	ASTM D 2240
Tear Strength	95	kN/m	ASTM D 624
Tensile Strength	35	MPa	ASTM D 412
Elongation at Break	480	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Glass Transition Temperature	-38	°C	ASTM E 1356

Other properties	Value	Unit	Test Standard
Density	1130	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Transparent

Regional Availability

North America, Europe, Asia Pacific

Applications

Automotive, Electrical and Electronical