

CELSTRAN® TPU-CF40-01

TPU-CF40

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	28900	MPa	ISO 527
^[C] Stress at break	320	MPa	ISO 527
^[C] Strain at break	1.35	%	ISO 527
^[C] Charpy notched impact strength, +23°C	41	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1380	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets