

**CELSTRAN® TPU-GF40-04 AF3001 Natural**

TPU-GLF40

Celanese

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>11300</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>225</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>2.55</b>	%	ISO 527
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>39</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1520</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets, Natural Color

**Special Characteristics**

Heat stabilized or stable to heat

**Features**

Long fiber reinforced

**Regional Availability**

North America, Europe, Asia Pacific