

CELSTRAN® TPU-GF50-01 AF3001 Natural

TPU-GLF50

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	14500	MPa	ISO 527
^[C] Stress at break	240	MPa	ISO 527
^[C] Strain at break	2.2	%	ISO 527
^[C] Charpy notched impact strength, +23°C	60	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1630	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Long fiber reinforced

Delivery form

Pellets, Natural Color

Regional Availability

North America, Europe, Asia Pacific