

CELSTRAN® TPU-GF60-01 AF3001 Natural

TPU-GLF60

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	18100	MPa	ISO 527
^[C] Stress at break	255	MPa	ISO 527
^[C] Strain at break	1.9	%	ISO 527
^[C] Charpy notched impact strength, +23°C	72	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1760	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Natural Color

Features

Long fiber reinforced

Regional Availability

North America, Europe, Asia Pacific