

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	850	MPa	ASTM D 638
Tensile Strength at Yield	34	MPa	ASTM D 638
Elongation at Break	40	%	ASTM D 638
Flexural Modulus	850	MPa	ASTM D 790
Flexural Strength	40	MPa	ASTM D 790
Shore D Hardness	60	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	62	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1300	kg/m ³	ASTM D 792

Characteristics

Applications

Automotive

Regional Availability

North America