

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	5495	MPa	ASTM D 638
Tensile Strength	96.5	MPa	ASTM D 638
Flexural Modulus	4495	MPa	ASTM D 790
Flexural Strength	127	MPa	ASTM D 790
Shore D Hardness	80	-	ASTM D 2240
Izod Impact notched, 1/8 in	427	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	181	J/m	ASTM D 256
Temperature	-40	°C	-

Other properties	Value	Unit	Test Standard
Density	1660	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets