

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	18	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	19	MPa	ISO 527
Flexural modulus, 23°C	1650	MPa	ISO 178
Izod notched impact strength, +23°C	40	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	3	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-40	°C	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	95	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	1020	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Injection Molding

#### Features

Copolymer

#### Delivery form

Pellets

#### Applications

Automotive

#### Special Characteristics

High impact or impact modified

#### Regional Availability

Europe