

Carbothane® Aliphatic PC-3595A-B20

TPU-Z20

The Lubrizol Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.01	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	46.88	MPa	ASTM D 790
Shore A Hardness	92	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	52.8	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1350	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Chemical Resistance

General Chemical Resistance, Oxidation Resistance, Radiation Resistance

Applications

Medical

Regional Availability

North America, Europe, Asia Pacific