

Tecoflex® MG-8020-B20

TPU-Z20

The Lubrizol Corporation

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ASTM Data | | | |
| Mold Shrinkage, MD | 0.011 | mm/mm | ASTM D 955 |

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Flexural Modulus | 1276 | MPa | ASTM D 790 |
| Shore D Hardness | 75 | - | ASTM D 2240 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1300 | kg/m ³ | ASTM D 792 |

Characteristics**Processing**

Injection Molding

Applications

Medical

Chemical Resistance

Radiation Resistance

Regional Availability

North America, Europe, Asia Pacific