

Tecothane® TT-2075D-B20

TPU-Z20

The Lubrizol Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	1310	MPa	ASTM D 790
Shore D Hardness	77	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1400	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Applications

Medical

Chemical Resistance

General Chemical Resistance, Radiation Resistance

Regional Availability

North America, Europe, Asia Pacific