

NPW TEX 250

TPU-Z30

Natureplast

Product Texts

Filler: 30 % Leather

Processing/Physical Characteristics**Value****Unit****Test Standard****ISO Data**

Melt flow index, MFI

3.1

g/10min

ISO 1133

Temperature

190

°C

-

Load

2.16

kg

-

Mechanical properties**Value****Unit****Test Standard****ISO Data**

Tensile Modulus

55

MPa

ISO 527

Charpy impact strength, +23°C

NkJ/m²

ISO 179/1eU

Strain at break TPE

600

%

ISO 527

Shore D hardness

33

-

ISO 7619-1

Characteristics**Processing**

Injection Molding

Applications

Packaging

Certifications

Contains renewable resources

Regional Availability

Europe