

RTP 1200 T-70A Z NATURAL

TPU

RTP Company

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	3.03	MPa	ASTM D 412
Shore A Hardness	70	-	ASTM D 2240
Tear Strength	61.3	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	1060	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Time	2 - 4	h	-
Melt temperature	188 - 199	°C	-
Mold temperature	15.6 - 37.8	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific