

Tecoflex® EG-72D

TPU

The Lubrizol Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Flexural Modulus	634.3	MPa	ASTM D 790
Shore D Hardness	67	-	ASTM D 2240
Other properties			
Density	1110	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Regional Availability

North America, Europe, Asia Pacific

Applications

Medical