

Tecoflex® SG-80A

TPU

The Lubrizol Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.01	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Flexural Modulus	6.895	MPa	ASTM D 790
Shore A Hardness	72	-	ASTM D 2240
Other properties			
Density	1040	kg/m ³	ASTM D 792

Characteristics**Applications**

Medical

Regional Availability

North America, Europe, Asia Pacific