

**Tecophilic® HP-60D-35**

TPU

The Lubrizol Corporation

| <b>Mechanical properties</b> | <b>Value</b> | <b>Unit</b> | <b>Test Standard</b> |
|------------------------------|--------------|-------------|----------------------|
| <b>ASTM Data</b>             |              |             |                      |
| Flexural Modulus             | <b>27.58</b> | MPa         | ASTM D 790           |
| Shore D Hardness             | <b>42</b>    | -           | ASTM D 2240          |

| <b>Other properties</b> | <b>Value</b> | <b>Unit</b>       | <b>Test Standard</b> |
|-------------------------|--------------|-------------------|----------------------|
| Density                 | <b>1120</b>  | kg/m <sup>3</sup> | ASTM D 792           |

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Regional Availability**

North America, Europe, Asia Pacific

**Applications**

Medical