

Tecothane® TT-1075D-M

TPU

The Lubrizol Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Flexural Modulus	1241	MPa	ASTM D 790
Shore D Hardness	75	-	ASTM D 2240
Other properties			
Density	1190	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Applications

Medical

Chemical Resistance

General Chemical Resistance

Regional Availability

North America, Europe, Asia Pacific