

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	20	MPa	ISO 37
Strain at break	600	%	ISO 37
Compression set at 70 °C, 24h	45	%	ISO 815
Abrasion resistance	40	mm ³	ISO 4649
Shore A hardness	70	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1180	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	180 - 200	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, South and Central America

Delivery form

Natural Color