

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-----------------|----------------------|
| ISO Data | | | |
| Tensile Strength | 25 | MPa | ISO 527 |
| Strain at break | 550 | % | ISO 527 |
| Tear strength | 60 | kN/m | ISO 34-1 |
| Abrasion resistance | 45 | mm ³ | ISO 4649 |
| Shore A hardness | 85 | - | ISO 7619-1 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1200 | kg/m ³ | ISO 1183 |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|--|------------------|-------------|----------------------|
| Pre-drying - Temperature | 80 | °C | - |
| Pre-drying - Time | 3 - 4 | h | - |
| Melt temperature | 210 - 230 | °C | - |

Characteristics

Processing
Injection Molding, Other Extrusion

Chemical Resistance
Hydrolytically Stable

Delivery form
Natural Color

Regional Availability
North America, Europe, South and Central America