

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	18	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	18.5	MPa	ISO 527
Flexural modulus, 23°C	1650	MPa	ISO 178
Charpy notched impact strength, +23°C	40	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	35	kJ/m ²	ISO 180/1A
Izod notched impact strength	3	kJ/m ²	ISO 180/1A
Temperature	-40	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	95	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1020	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Features

Copolymer

Applications

Automotive

Regional Availability

Europe