

**Product Texts**

Flame retardant thermoplastic vulcanizate (TPV)

Flammability @3.2mm nom. thickn. V-0 -

Flammability @1.6mm nom. thickn. V-0 -

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Stress at 100% elongation	3.7	MPa	ISO 527
<sup>[C]</sup> Stress at 300% elongation	4.5	MPa	ISO 527
<sup>[C]</sup> Compression set at 70 °C, 24h	59	%	ISO 815

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	1270	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Special Characteristics**

Flame retardant

**Delivery form**

Black