

FORPRENE® 6ESD01A30 NEUTRO

TPV

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 100% elongation	0.7	MPa	ISO 527
^[C] Stress at 300% elongation	1.4	MPa	ISO 527
^[C] Compression set at 70 °C, 24h	34	%	ISO 815

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	905	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Delivery form**

Natural Color