

FORPRENE® 6ESD01A55 NEUTRO

TPV

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 100% elongation	1.5	MPa	ISO 527
^[C] Stress at 300% elongation	2.3	MPa	ISO 527
^[C] Compression set at 70 °C, 24h	34	%	ISO 815

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	973	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Delivery form**

Natural Color