

FORPRENE® 6IE901A90 NERO

TPV

Celanese

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.2	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.8	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	87.3	MPa	ISO 527
^[C] Stress at 100% elongation	4.8	MPa	ISO 527
^[C] Compression set at 70 °C, 24h	51	%	ISO 815

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	960	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding, Profile Extrusion

Special Characteristics

U.V. stabilized or stable to weather

Delivery form

Black