

FORPRENE® 6K5901A65 NERO

TPV

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 100% elongation	2.4	MPa	ISO 527
^[C] Stress at 300% elongation	3.7	MPa	ISO 527
^[C] Compression set at 70 °C, 24h	35	%	ISO 815

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	977	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Delivery form**

Black