

**FORPRENE® 6M0001A75 NEUTRO**

TPV

Celanese

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Stress at 100% elongation	<b>3.2</b>	MPa	ISO 527
<sup>[C]</sup> Stress at 300% elongation	<b>4.6</b>	MPa	ISO 527
<sup>[C]</sup> Compression set at 70 °C, 24h	<b>48</b>	%	ISO 815

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>970</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Delivery form**

Natural Color