

| Mechanical properties | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ISO Data | | | |
| ^[C] Stress at 100% elongation | 8.6 | MPa | ISO 527 |
| ^[C] Stress at 300% elongation | 9.2 | MPa | ISO 527 |
| ^[C] Compression set at 70 °C, 24h | 41 | % | ISO 815 |
| ^[C] Shore D hardness | 42 | - | ISO 7619-1 |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| ^[C] Density | 959 | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics**Delivery form**

Black