

FORPRENE® 6MD49XA82 GRIGIO

TPV

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 100% elongation	4.1	MPa	ISO 527
^[C] Stress at 300% elongation	5.6	MPa	ISO 527
^[C] Compression set at 70 °C, 24h	54	%	ISO 815

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	960	kg/m ³	ISO 1183

[C]: CAMPUS