

FORPRENE® 6NB901A90 NERO

TPV

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 100% elongation	6.9	MPa	ISO 527
^[C] Stress at 300% elongation	8.4	MPa	ISO 527
^[C] Compression set at 70 °C, 24h	54	%	ISO 815
^[C] Shore D hardness	36	-	ISO 7619-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	958	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Blow Molding

Delivery form

Black