

**FORPRENE® 6NB901D40 NERO**

TPV

Celanese

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Stress at 100% elongation	<b>7.9</b>	MPa	ISO 527
<sup>[C]</sup> Stress at 300% elongation	<b>8.7</b>	MPa	ISO 527
<sup>[C]</sup> Compression set at 70 °C, 24h	<b>56</b>	%	ISO 815
<sup>[C]</sup> Shore D hardness	<b>39</b>	-	ISO 7619-1

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>954</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Blow Molding

**Delivery form**

Black