

**FORPRENE® 6NM901A50 NERO**

TPV

Celanese

| <b>Mechanical properties</b>                 | <b>Value</b> | <b>Unit</b> | <b>Test Standard</b> |
|--|--------------|-------------|----------------------|
| <b>ISO Data</b>                              |              |             |                      |
| <sup>[C]</sup> Stress at 100% elongation     | <b>1.7</b>   | MPa         | ISO 527              |
| <sup>[C]</sup> Stress at 300% elongation     | <b>3</b>     | MPa         | ISO 527              |
| <sup>[C]</sup> Compression set at 70 °C, 24h | <b>33</b>    | %           | ISO 815              |

[C]: CAMPUS

| <b>Other properties</b> | <b>Value</b> | <b>Unit</b>       | <b>Test Standard</b> |
|-------------------------|--------------|-------------------|----------------------|
| <sup>[C]</sup> Density  | <b>957</b>   | kg/m <sup>3</sup> | ISO 1183             |

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Delivery form**

Black