

**FORPRENE® 6NM901A65 NERO**

TPV

Celanese

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>27.5</b>	MPa	ISO 527
<sup>[C]</sup> Stress at 100% elongation	<b>2.4</b>	MPa	ISO 527
<sup>[C]</sup> Stress at 300% elongation	<b>4</b>	MPa	ISO 527
<sup>[C]</sup> Compression set at 70 °C, 24h	<b>27</b>	%	ISO 815
<sup>[C]</sup> Compression set at 100 °C, 24h	<b>48</b>	%	ISO 815

[C]: CAMPUS

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Glass transition temperature, 10°C/min	<b>-58.6</b>	°C	ISO 11357-1/-2

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>950</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Delivery form**

Black