

FORPRENE® 6SD001A30 NEUTRO

TPV

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 100% elongation	0.7	MPa	ISO 527
^[C] Stress at 300% elongation	1.5	MPa	ISO 527
^[C] Compression set at 70 °C, 24h	22	%	ISO 815

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Coeff. of linear therm. expansion, parallel	186	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	329	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	900	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color