

FORPRENE® 6SD004A60 NEUTRO

TPV

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at 100% elongation	1.7	MPa	ISO 527
^[C] Stress at 300% elongation	2.6	MPa	ISO 527
^[C] Compression set at 70 °C, 24h	46	%	ISO 815

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	970	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding, Other Extrusion

Delivery form

Natural Color