

**GEOLAST™ 701-80W183**

TPV

Celanese

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	<b>3.5</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	<b>4.0</b>	%	ISO 294-4, 2577

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	<b>1</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1030</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding, Profile Extrusion, Sheet Extrusion, Blow Molding

**Regional Availability**

North America, Europe, South and Central America, Near East/Africa

**Delivery form**

Pellets