

**GEOLAST™ 703-45**

TPV

Celanese

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	<b>6.0</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	<b>5.0</b>	%	ISO 294-4, 2577

[C]: CAMPUS

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Shore D hardness	<b>47</b>	-	ISO 7619-1

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>980</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding, Profile Extrusion, Sheet Extrusion, Blow Molding

**Regional Availability**

North America, South and Central America

**Delivery form**

Pellets