

PL108NT-I
(PE-HD)

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	8.5	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Other properties			
Density	950	kg/m ³	ISO 1183
Processing Recommendation Extrusion			
Feed temperature	30 - 50	°C	-
Zone 1	140 - 160	°C	-
Zone 2	160 - 180	°C	-
Zone 3	180 - 200	°C	-

Characteristics

Processing

Wire/Cable Extrusion

Delivery form

Natural Color

Additives

Lubricants

Features

Tribologic Grade

Certifications

RoHS compliant

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa