

Lotrène® LA 0710

(PE-LD)

QAPCO

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	107	°C	ASTM D 3418
Vicat Temperature	86	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	918	kg/m ³	ASTM D 792

Characteristics**Processing**

Coating

Certifications

Food contact, Food approval FDA 21 CFR

Features

Good Adhesion, Heat Sealable, Low Neck-In, Low Odor

Regional Availability

Asia Pacific, Near East/Africa