

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	6	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Other properties	Value	Unit	Test Standard
Density	926	kg/m <sup>3</sup>	ASTM D 792

Film Properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break, MD	30	MPa	ASTM D 882
Tensile Strength at Break, TD	18	MPa	ASTM D 882
Elongation at Break, MD	900	%	ASTM D 882
Elongation at Break, TD	800	%	ASTM D 882
Type of extrusion	blown	-	-
Thickness of specimen	0.03	mm	-

## Characteristics

### Processing

Film Extrusion

### Delivery form

Pellets

### Additives

Antiblocking agent

### Special Characteristics

Transparent

### Features

Low Odor, Copolymer, Butene Copolymer

### Certifications

Food contact, Food approval FDA 21 CFR

### Applications

Packaging

### Regional Availability

Asia Pacific