

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.24	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	16	MPa	ISO 527
Strain at break	>50	%	ISO 527

Other properties	Value	Unit	Test Standard
Density	944	kg/m ³	ISO 1183

Characteristics

Processing

Pipe/Tube Extrusion, Other Extrusion

Delivery form

Pellets, Black

Special Characteristics

U.V. stabilized or stable to weather

Chemical Resistance

Environmental Stress Crack Resistance

Regional Availability

Asia Pacific