

PCR.202041

(PE-LLD)

Oceanworks, Inc.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3.13	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	13	MPa	ISO 527
Other Standards^[5]			
Strain at break	300	%	

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	920	kg/m ³	ISO 1183

Characteristics**Processing**

Film Extrusion

Delivery form

Pellets

Special Characteristics

Transparent

Certifications

Recycled Resin Content, Post-Consumer Recyclate

Regional Availability

North America, Europe, Asia Pacific