

VICTREX® PEEK 150FC30

(PEEK+PTFE)-(CF+CD)30

Victrex plc

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
Thermal conductivity of melt	0.85	W/(m K)	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	13500	MPa	ISO 527
Stress at break	160	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus, 23°C	12000	MPa	ISO 178
Flexural strength	230	MPa	ISO 178
Charpy impact strength, +23°C	30	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	30	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	5.5	kJ/m ²	ISO 180/1A
Shore D hardness	83	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	343	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	143	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	315	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	12	E-6/K	ISO 11359-1/-2
Oxygen index	43	%	ISO 4589-1/-2
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1000000	Ohm*m	IEC 62631-3-1

Other properties	Value	Unit	Test Standard
Water absorption	0.3	%	Sim. to ISO 62
Density	1450	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 150	°C	-
Pre-drying - Time	3 - 5	h	-
Processing humidity	≤0.02	%	-
Feed temperature	≤100	°C	-
Zone 1	360	°C	-
Zone 2	365	°C	-
Zone 3	370	°C	-
Zone 4	375	°C	-
Nozzle temperature	380	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Black

Chemical Resistance

General Chemical Resistance

Certifications

Food contact, Food approval FDA 21 CFR

Features

Tribologic Grade

Regional Availability

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa