

RTP 2200 AR 15 TFE 15
(PEEK+PTFE)-AF

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.008	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	5378	MPa	ASTM D 638
Tensile Strength	82.7	MPa	ASTM D 638
Flexural Modulus	5240	MPa	ASTM D 790
Flexural Strength	138	MPa	ASTM D 790
Izod Impact notched, 1/8 in	42.7	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	163	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1400	kg/m ³	ASTM D 792
Moisture Content	0.1	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	3	h	-
Melt temperature	349 - 399	°C	-
Mold temperature	163 - 218	°C	-
Injection pressure	82.7 - 124	MPa	-

Characteristics

Processing

Injection Molding

Additives

Lubricants

Regional Availability

North America, Europe, Asia Pacific