

Product Texts

LNP LUBRICOMP LCL33 compound is based on Polyetheretherketone (PEEK) resin containing 15% carbon fiber, 15% PTFE. Added features of this grade include: Wear Resistant, Electrically Conductive.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	7	cm ³ /10min	ISO 1133
Temperature	400	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	14500	MPa	ISO 527
Stress at break	162	MPa	ISO 527
Strain at break	2.9	%	ISO 527
Flexural modulus	11700	MPa	ISO 178
Izod impact strength, +23°C, 4mm	34	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	7	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	300	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	9.5	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	53	E-6/K	ISO 11359-1/-2

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	100000	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1430	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 150	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.1	%	-
Melt temperature	380 - 390	°C	-
Mold temperature	140 - 165	°C	-
Zone 1	350 - 360	°C	-
Zone 2	365 - 375	°C	-
Zone 3	380 - 395	°C	-
Screw speed	60 - 100	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Special Characteristics

Increased electrical conductivity