

Product Texts

LNP LUBRICOMP LCL33E compound is based on Polyetheretherketone (PEEK) resin containing 15% carbon fiber, 15% PTFE. Added features of this grade include: Easy Molding, Wear Resistant, Electrically Conductive.

UL Yellow Card Link [E121562-101283895](https://www.ulprospector.com/121562-101283895)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	0.2	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.55	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	14700	MPa	ISO 527
Stress at break	187	MPa	ISO 527
Strain at break	1.6	%	ISO 527
Flexural modulus	11700	MPa	ISO 178
Flexural strength	230	MPa	ISO 178
Izod impact strength, +23°C, 4mm	34	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	6	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	16610	MPa	ASTM D 638
Tensile Strength at Break	179	MPa	ASTM D 638
Elongation at Break	1.7	%	ASTM D 638
Flexural Modulus	12960	MPa	ASTM D 790
Flexural Strength	266	MPa	ASTM D 790
Izod Impact notched, 1/8 in	64	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	491	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	240	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	V-0 1.5	class mm	IEC 60695-11-10 -
ASTM Data			
DTUL @ 264 psi	298	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Humidity absorption	0.7	%	Sim. to ISO 62
Density	1430	kg/m ³	ISO 1183
Water Absorption, 24hr	0.07	%	ASTM D 570
Density	1430	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	150	°C	-
Pre-drying - Time	4 - 6	h	-
Mold temperature	175 - 190	°C	-
Zone 1	370 - 380	°C	-
Zone 2	380 - 400	°C	-
Zone 3	380 - 400	°C	-
Screw speed	60 - 100	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Increased electrical conductivity