

RTP 2205 LF TFE 15 Z
(PEEK+PTFE)-GF30

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0035	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	12760	MPa	ASTM D 638
Tensile Strength	159	MPa	ASTM D 638
Flexural Modulus	11030	MPa	ASTM D 790
Flexural Strength	234	MPa	ASTM D 790
Izod Impact notched, 1/8 in	133	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.59	mm	-
Electrical properties			
ASTM Data			
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Other properties			
Density	1640	kg/m ³	ASTM D 792
Moisture Content	0.1	%	-
Processing Recommendation Injection Molding			
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	3	h	-
Melt temperature	349 - 399	°C	-
Mold temperature	163 - 218	°C	-
Injection pressure	82.7 - 124	MPa	-

Characteristics

Processing

Injection Molding

Certifications

Food contact, Food approval FDA 21 CFR

Additives

Lubricants

Regional Availability

North America, Europe, Asia Pacific