

**Product Texts**

LNP LUBRICOMP EFL36 compound is based on Polyetherimide (PEI) resin containing 30% glass fiber, 15% PTFE. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E45329-101283857](https://www.ul.com/yellow-card/E45329-101283857)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	4	cm <sup>3</sup> /10min	ISO 1133
Temperature	345	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
Molding shrinkage, normal	0.3	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Stress at break	168	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus	9000	MPa	ISO 178
Izod impact strength, +23°C, 4mm	35	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	10	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	204	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	28	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	40	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Other properties	Value	Unit	Test Standard
Humidity absorption	0.18	%	Sim. to ISO 62
Density	1620	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	150	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	360 - 375	°C	-
Mold temperature	140 - 180	°C	-
Zone 1	355 - 365	°C	-
Zone 2	360 - 370	°C	-
Zone 3	365 - 375	°C	-
Back pressure	0.3 - 0.7	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Europe